

# EPOXY PRIMER

## Kemikaliebestandighed

Denne liste er lavet på grundlag af laboratorietests.

### Tegnforklaring:

- \*\* Bestandig
- \* Midlertidig bestandig
- Ikke bestandig

Acetone	-
Aluminiumhydroxid	**
Aminer	-
Ammoniak 10-25%	**
Aromatiske kulbrinter	**
Dieselolie	**
Benzen	**
Benzin	**
Borsyre 3% v. 30°C	**
Butanol	*
Butylether	**
Butylacetat	*
Citronsyre 30%	**
Cyclohexan	**
Destilleret vand	**
Dibutylphthalat	**
Dioktylphthalat	**
Druesaft 20% v. 80°C	**
Eddikesyre 1%	**
Eddikesyre 5%	-
Ethanol (sprit) 96%	*
Ethanol (sprit) 10 %	**
Ethylacetat	-
Ethylenglycol	**
Fedtsyrer	*
Fiskeolie	**
Fedt, animalsk	**
Formaldehyd 35%	**
Fosforsyre 5-10%	*
Fosforsyre 20%	-
Fremkaldervæske 1:10	**
Glycerin	**
Grøntsagssaft	**

Heptan	**
Hexan	**
Hydrogenperoxid 3% (brintoverilte )	**
Isopropanol	*
Jet-benzin	**
Kaliumhydroxid	**
Kalk	**
Kloroform	-
Klorvand	*
Kromsyre 5-40%	**
Kølevæske	**
Linolie	**
Melasse	**
Methanol	-
Methylchlorid	-
Mineralolie	**
Mineralsk terpentin	**
Myresyre 85%	-
Myresyre 1%	*
Myresyre 0,1%	**
Myresyre pH=4	**
Mælk	**
Mælkesyre 1%	**
Monochlorbenzen	*
Natriumcarbonat	**
Natriumchlorid 3-30%	**
Natriumchlorid konc. opløsning	**
Natriumhydroxid 10%	**
Natriumhydroxid 50% v. 50°C	**
Natriumhypochlorit 16 % med 12 % NaCl	*

2-Nitro-propan	*
n-Propanol	*
n-Propylacetat	*
Olivenolie	**
Oxalsyre 10%	**
Perchloretylen	**
Petroleum	**
Phenol	-
Ricinusolie	**
Råolie	**
Salpetersyre 5%	**
Salpetersyre 10%	*
Salpetersyre 20-60%	-
Saltsyre 5-20%	**
Saltsyre 30%	*
Saltsyre 37% ( konc. )	-
Siliconeolie	**
Smørsyre 1%	**
Sne	**
Styren	*
Svovlsyre 5-80%	*
Svovlsyre, rygende	-
Sæbe 5% vandig opløsning	**
Tetrachlormethan	*
Toluen	**
Trichlorethylen	*
Valle	**
Vin	**
Whisky	*
Xylen	**
Øl	**